

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

Claims 1-10 (canceled)

11. (Previously presented) A method for fabricating a liquid crystal device having polymer micro-structures, the method comprising the steps of:

preparing a mixture comprising a liquid crystal material and a prepolymer;

providing a first and second cell wall structure, said first and second cell wall structures optionally having electrodes disposed on facing sides of said first and second cell wall structures, and, optionally having an alignment layer disposed on at least one of said electrodes;

disposing said mixture into a space between the first and second cell wall structures;

causing said liquid crystal material to assume a predetermined orientation with a non-uniform spatially distorted director field; and

exposing said mixture to conditions which cause polymerization of the prepolymer and formation of polymer micro-structures between the cell walls, wherein the micro-structures have a shape and spatial location determined by a director field of said liquid crystal material.

12. (Original) A method for fabricating a liquid crystal device having polymer micro-structures according to claim 11, wherein said mixture comprising a liquid crystal material and a prepolymer comprises between about 0.1 percent and about 50 percent prepolymer.

13. (Previously presented) A method for fabricating a liquid crystal device having polymer micro-structures according to claim 11, wherein said liquid crystal material is selected from the group consisting of cholesteric liquid crystal material, nematic liquid crystal material, columnar liquid crystal material and smectic liquid crystal material.

14. (Previously presented) A method for fabricating a liquid crystal device having polymer micro-structures according to claim 11, wherein said prepolymer is selected from the group consisting of UV-curable prepolymers and heat-curable prepolymers.

15. (Previously presented) A method for fabricating a liquid crystal device having polymer micro-structures according to claim 11, wherein said first and second cell wall structures have electrodes disposed thereon, and wherein said step of causing said liquid crystal material to assume a predetermined orientation with a non-uniform spatially distorted director field comprises applying a voltage across said electrodes.

16. (Previously presented) A method for forming polymer micro-structures, the method comprising the steps of:

- preparing a mixture comprising a liquid crystal material and a prepolymer;

- providing a first and second cell wall structure;

- disposing said mixture into a space between the first and second cell wall structures;

- causing said liquid crystal material to assume a predetermined orientation with a non-uniform spatially distorted director field; and

- exposing said mixture to conditions which cause polymerization of the prepolymer and formation of polymer micro-structures between the cell walls, wherein the micro-structures have a shape and spatial location determined by a director field of said liquid crystal material.

17. (Previously presented) The method for forming polymer micro-structures according to claim 16, wherein the prepolymer is a UV-curable prepolymer and wherein the step of exposing the mixture to conditions which cause polymerization of the prepolymer comprises exposing the prepolymer to UV radiation.

18. (Previously presented) The method for forming polymer micro-structures according to claim 16, wherein the first and second cell wall structures additionally comprise electrodes disposed on facing sides of said first and second cell wall structures.

19. (Previously presented) The method for forming polymer micro-structures according to claim 16, wherein at least one of said first and second cell wall structures additionally comprise an alignment layer disposed thereon.

20. (Previously presented) The method for forming polymer micro-structures according to claim 16, wherein said mixture comprising a liquid crystal material and a curable prepolymer comprises between about 0.1 percent and about 50 percent curable prepolymer.

21. (Previously presented) The method for forming polymer micro-structures according to claim 16, wherein said liquid crystal material is selected from the group consisting of nematic liquid crystal material, cholesteric liquid crystal material, columnar liquid crystal material and smectic liquid crystal material.

22. (Previously presented) A method for forming a liquid crystal cell comprising the method for forming polymer micro-structures according to claim 16.

23. (Previously presented) A liquid crystal cell formed by the method of claim 16.